



COMPOSITION

Cork granules (1–2 mm), thermoplastic resin binder

BENEFITS

- Good sealing
- Good resistance to hydrocarbons
- Good temperature resistance
- Good mechanical properties
- Option to insert fabric reinforcement for improved tensile strength

- Light

APPLICATIONS

- Industrial sealing
- Automotive industry
- Railway industrie
- Energy production

FORMATS

Dimensions	Tolerance	Thickness	Tolerance
1000 x 500	+/-0.50	1 à 4	+/-0.50
1000 x 600	+/-0.50	5 à 10	+/-0.50
1000 x 700	+/-0.50	> 10	+/-0.50

TECHNICAL DATA

Description	Standard	Unit	Value
Density	NF-T 46-002	kg/m ³	215
Compressibility (ASTM test at 100 psi)	ASTM F36	%	32
Recovery (ASTM test at 100 psi)	ASTM F36	%	84
Tensile strength	NF-T 46-007	daN/cm ²	7
Elongation before break	-	%	17.8

PRESERVATION AND STORAGE

12 months under storage conditions of 20°C ± 3°C and 60% ± 5% relative humidity.

The technical specifications mentioned above are typical average values obtained using the indicated test methods and are therefore subject to normal manufacturing variations. They are provided for information purposes only. They do not constitute a guarantee, and we recommend conducting a trial before final application.