



COMPOSITION

Composed of cork granules (0.50 to 1.00 mm) and NBR binder.

BENEFITS

- Elastic recovery
- Gas certification (DIN 3535-5 Part5)
- Reduces material creep thanks to the addition of cork
- Easily adapts to surface irregularities
- Limits fastener distortion
- Light

APPLICATIONS

- Boilers
- Gas valve blocks
- Controllers
- Valves

FORMATS

Dimensions (mm)	Tolerances (mm)	Thickness (mm)	Tolerances (mm)
1000 x 1000	+/-2.00	< 1.6	+/-0.25
		≥ 1.6 à < 6.0	+/-0.38
		≥ 6.0 à < 10.0	+/-0.50
		≥ 10.0 à < 15.0	+/-0.75
		≥ 15.0	+/-1.00

TECHNICAL DATA

Test description	Standard	Unit	Value
Density	ASTM F1315	kg/m ³	700 - 900
Hardness	ISO 48	Shore A	65
Compressibility (ASTM test at 400 psi)	ASTM F36	%	25 - 40
Recovery	ASTM F36	%	75
Tensile strength	ISO 37	%	40
Elongation before break	-	°C	125

PRESERVATION AND STORAGE

12 months under storage conditions of 20°C ± 3°C and 60% ± 5% relative humidity.

The technical specifications mentioned above are typical average values obtained using the indicated test methods and are therefore subject to normal manufacturing variations. They are provided for information purposes only. They do not constitute a guarantee, and we recommend conducting a trial before final application.